

Casting Resin

RenCast[®] 5146 A / 5146 B

Mass Casting Polyurethane system

Key properties

- Mass casting system used in combination with Filler DT 082
- Low exotherm and minimal shrinkage, even in thick sections

Applications

- Sheet metal forming tools for steel and aluminium
- Negative moulds and tooling fixtures
- Large volume moulds for the ceramics industry

Product data

Property	Unit	RenCast 5146 A	RenCast 5146 B
Appearance Colour	visual	Liquid Light yellow	Liquid Opaque beige
Viscosity at 25°C	m Pa s	18 - 35	1700 - 2100
Density	g/cm ³	1.2	1.1

Processing

Mix ratio	Parts by weight (Unfilled, face casting up to 20 mm)	Parts by weight (Filled, full casting to 300 mm)
RenCast 5146 A	80	80
RenCast 5146 B	100	100
Filler DT 082	-	360 - 420

Mix the A and B components thoroughly in the ratio indicated. Then mix the filler thoroughly into the A/B mix in the ratio indicated. Degassing the material prior to cure and post curing the mix will improve final properties.

For Mass Casting Options, please refer to publication no.

Properties

Resin/Hardener mix:	Volume	Unit	RenCast 5146 A RenCast 5146 B (unfilled)	RenCast 5146 A RenCast 5146 B Filler DT 082
Appearance			thin, milky liquid	high-viscosity cream liquid
Viscosity at 25°C		mPa s	1500-2000	Thick pourable paste
Pot life at 25°C	3kg	min	20-30	30-40
Max. Layer thickness		mm	20	300
Demoulding time		h	8 - 14	15-20

After cure: 7 days at 25°C or 14 hours at 40°C

Density	ISO 1183	g/cm ³	1.2	1.6
Hardness	ISO 868	Shore D	80	85
Coefficient of thermal expansion	ISO 11359	10 ⁻⁶ K ⁻¹	100	45
Deflection temperature	ISO 75	°C	75 - 80	75 - 80
Compressive strength	ISO 604	MPa	85 - 90	90 - 95
Compressive modulus	ISO 604	MPa	3000	9500
Flexural strength	ISO 178	MPa	Not Measured	Not Measured
Linear shrinkage		mm/m	2.0	0.6

Storage

The resin and hardeners described in this instruction sheet have the shelf lives shown provided they are stored at 6 - 28°C in a dry place and sealed containers, preferably those in which they are supplied.

Working condition

The product should be used when within the temperature range 18-25°C and should not be used in high humidity.
Shake the B component prior to use.

Packaging

System	RenCast 5146 A	RenCast 5146 B	Filler
Quantity and Weight	1000, 180 or 20 kg	1000, 200 or 25 kg	1000 or 15 kg
Quantity and Weight	4 x 4 kg		

Handling precautions

Caution

Our products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed. The uncured materials must not, for instance, be allowed to come into contact with foodstuffs or food utensils, and measures should be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The wearing of impervious rubber or plastic gloves will normally be necessary; likewise the use of eye protection. The skin should be thoroughly cleansed at the end of each working period by washing with soap and warm water. The use of solvents is to be avoided. Disposable paper - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. These precautions are described in greater detail in the Material Safety Data sheets for the individual products and should be referred to for fuller information.

Huntsman Advanced Materials (UK) Limited

All recommendations for the use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefore. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

Duxford, Cambridge
England CB2 4QA

Tel: +44 (0) 1223 493 000
Fax: +44 (0) 1223 493 002

www.renshape.com

© 2004 Huntsman Advanced Materials (Switzerland) GmbH

® Ren, RenShape, RenPaste, RenGel, RenLam, RenCast, RenRelease, RenPIM and Parts In Minutes are registered trademarks of Huntsman LLC or an affiliate thereof in one or more, but not all, countries.