

Casting Resin

RenCast® FC 52 Isocyanate / FC 52 Polyol

Quick setting polyurethane system

Key properties

- · Beige coloured three-part system
- Designed for quick accurate castings
- · Can be cast in layer thickness up to 30 mm
- Filler content can be varied to suit application

Applications

- Moulds
- Holding fixtures
- Foundry patterns
- Replicas and Prototypes

Product data

Property	Unit	RenCast FC 52 Isocyanate	RenCast FC 52 Polyol
Appearance Colour	visual	Liquid Amber	Liquid Amber
Viscosity at 25°C	mPa s	20 - 30	65 – 75
Density	g/cm ³	1.12	0.98

Processing

Mix ratio	Parts by weight (unfilled system)	Parts by weight (filled)
RenCast FC 52 A	100	100
RenCast FC 52 B	100	100
Filler DT 082		300

Mix the two components thoroughly in the ratio indicated.

Degassed material will improve properties. Post-curing will improve final properties.

Properties

Resin/Hardener mix:	Volume	Unit	FC 52 Isocyanate FC 52 Polyol Unfilled	FC 52 Isocyanate FC 52 Polyol Filler DT 082
Appearance		visual	Beige unfilled	Beige filled
Viscosity at 25°C		mPa s	70	paste
Pot life at 25°C	(1000 ml)	min	6 - 8	10
Max. Layer thickness		mm	30	100
Demoulding time		min	60 - 90	180

After cure: 7 days at RT or 14 hours at 80 °C

Density	ISO 1183	g/cm ³	1	1.6
Hardness	ISO 868	Shore D	70 - 75	80 – 85
Deflection temperature	ISO 75	°C	80	85
Compressive strength	ISO 604	MPa	35	38
Compressive modulus	ISO 604	MPa	1000	2100
Flexural strength	ISO 178	MPa	25	26
Linear shrinkage @ 5 mm		mm/m	5	0
Linear shrinkage @ 10 mm		mm/m	5.5	0.1
Linear shrinkage @ 20 mm		mm/m	-	0.6

Storage

The resin and hardeners described in this instruction sheet have the shelf lives shown provided they are stored at 6 - 28°C in a dry place and sealed containers, preferably those in which they are supplied.

Working conditions

The product should be used when within the temperature range 18-25°C. Shake the unfilled and stir the filled system.

Packaging

System	RenCast FC 52 Isocyanate	RenCast FC 52 Polyol	
Quantity and Weight	1 x 20 kg	1 x 20 kg	
Quantity and Weight	1 x 5 kg	1 x 5 kg	
Quantity and Weight 4 x 1 kg 4 x 1 kg			
Filler DT 082 Multipacks of 6 x 1.5 kg and 15 kg containers			

Handling precautions

Caution

Our products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed. The uncured materials must not, for instance, be allowed to come into contact with foodstuffs or food utensils, and measures should be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The wearing of impervious rubber or plastic gloves will normally be necessary; likewise the use of eye protection. The skin should be thoroughly cleansed at the end of each working period by washing with soap and warm water. The use of solvents is to be avoided. Disposable paper - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. These precautions are described in greater detail in the Material Safety Data sheets for the individual products and should be referred to for fuller information.

Huntsman Advanced Materials (UK) Limited

All recommendations for the use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefore. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

Duxford, Cambridge England CB2 4QA

Tel: +44 (0) 1223 493 000 Fax: +44 (0) 1223 493 002

- © 2004 Huntsman Advanced Materials (Switzerland) GmbH
- ® Ren, RenShape, RenPaste, RenGel, RenLam, RenCast, RenLease, RenPIM and Parts In Minutes are registered trademarks of Huntsman LLC or an affiliate thereof in one or more, but not all, countries.

www.renshape.com